CLAIMS

1. A laminate (I) comprising a base layer (A) and an adhesive layer (B) formed on one side or both sides of the layer A, wherein

the layer A is a film made of (A-1) a wholly aromatic polyimide (PI^{A-1}) having a glass transition point of 350°C or higher or (A-2) a wholly aromatic polyamide (PA^{A-2}) having a glass transition point of 350°C or higher and having a linear thermal expansion coefficient of -10 ppm /°C to 10ppm/°C; and

the layer B comprises (B-1) a wholly aromatic polyimide (PI^{B-1}) having a glass transition point of 180°C or higher and lower than 350°C, (B-2) a wholly aromatic polyamide (PA^{B-2}) having a glass transition point of 180°C or higher and lower than 350°C, or (B-3) a resin composition (RC^{B-3}) comprising a wholly aromatic polyimide (PI^{B-3}) and a wholly aromatic polyamide (PA^{B-3}) having a glass transition point of 180°C or higher and lower than 350°C.

2. The laminate according to claim 1 which has two right-angled directions with a Young's modulus of more than 3 GPa in the plane.

3. The laminate according to claim 1, wherein the layer A is a film which has two right-angled directions with a Young's modulus of more than 10 GPa in the plane.

4. (cancelled)

5. The laminate according to claim 1, wherein the average thickness of the layer A is 50 μm or less.

6. The laminate according to claim 1, wherein the wholly